

## Declaration

I declare that this is my own work and this thesis with the title “**Reinforcement of carboxylated acrylonitrile-butadiene rubber latex films by surface modified fillers**” does not incorporate without acknowledgement any material previously submitted for a Degree or Diploma in any other University or Institute of higher learning and to the best of my knowledge and belief it does not contain any material previously published or written or orally communicated by another person except where due reference is made in the text.

Also, I hereby grant to University of Moratuwa the non-exclusive right to reproduce and distribute my thesis, in whole or in part in print, electronic or other medium. I retain the right to use this content in whole or part in future works (such as articles or books).

Signature of the candidate:

.....

Date:

The above candidate has carried out research for the Masters thesis under my supervision.

Signature of the supervisor:

.....

Date:

Dr. (Mrs.) N.M.V.K. Liyanage

## Abstract

Carboxylated acrylonitrile butadiene rubber (XNBR) latex is a widely used synthetic copolymer of acrylonitrile and butadiene with a small amount of a third monomer containing carboxylic groups. Some of the mechanical properties of XNBR latex are not adequate for certain applications and should be enhanced. Incorporation of reinforcing fillers is most widely used technique for that purpose. Silica filler is used in dry rubber industry as a reinforcement agent, but difficult to use in latex applications due to some problems associated with dispersing silica resulted by its surface chemistry. Surface of silica should be modified in order to use as a reinforcing filler in latex applications.

In the present investigation, XNBR latex was filled with a series of surface modified precipitated silica. Surface modification of silica was affected by two methods i.e. non aqueous medium modification and aqueous medium modification, with the use of some synthetic polymers (SP). Three types of SPs, containing hydrophilic and hydrophobic groups that are methacrylic acid and 2-ethyl hexyl acrylate, respectively in different ratios were synthesized and used at a concentration of 3 % by weight of silica for the modification. The effectiveness of the SPs in enhancing reinforcing ability of silica in XNBR latex films was evaluated through investigation of mechanical properties of a range of vulcanized films cast from filled XNBR latex compounds containing modified filler in different concentrations in the range of 5 to 20 phr loadings. One of the well known non-sulphur vulcanization systems of XNBR, crosslinking with zinc oxide was used during the study. Latex films were cast from filled latex by several routes with different process sequences in order to investigate the importance of each step of the process to find out the most suitable step for filler addition.

Some of the mechanical properties important for rubber latex applications, such as tear strength, of modified silica filled cast films improved over unmodified silica filled cast films. Optimum tear strength of cast films filled with modified fillers was observed at 20 phr filler loading, while films containing 15 phr filler loading gave optimum tensile properties. Morphological studies done by scanning electron microscopy illustrated improved distribution and lower size of modified filler particles within the XNBR matrix indicating surface modification has reduced filler aggregation.

SPs used for the modification are capable of enhancing reinforcing action of silica filler in XNBR latex films. The extent of enhancement of physical properties of filled cast films depends on the hydrophilic/hydrophobic ratio of SPs used for surface modification of silica. Highest physical properties were observed for the vulcanizates containing silica modified with the most hydrophobic SP, which is thought to be the result of better rubber filler interactions created by the entanglement of rubber chains with hydrophobic side groups present in this particular SP.

***Keywords— Carboxylated acrylonitrile butadiene rubber, synthetic polymer, silica filler***

## **Acknowledgment**

My foremost sincere gratitude is expressed to my supervisor, Dr. (Mrs.) N.M.V.K. Liyanage, Senior Lecturer, Department of Materials Science and Engineering, University of Moratuwa, who gave me the opportunity to carry out this research work and for the immense help and guidance given throughout the project work.

I would like to thank Dr. S.U. Adikary, Head of the Department of Materials Science and Engineering, University of Moratuwa, for allowing me to conduct the research work in the department. I would also like to thank Dr. P.G. Rathnasiri, Head of the Department of Chemical and Process Engineering, University of Moratuwa, for allowing me to use the laboratory facilities in their department.

I am also grateful to progress review committee chair, Dr.(Mrs) A.H.L.R. Nilmini, Head of Polymer Chemistry Department, Rubber Research Institute, and, progress review committee member, Dr.(Mrs) Shantha Egodage, Senior Lecturer, Department of Chemical and Process Engineering, University of Moratuwa, for providing correct guidance through the project work.

I also like to express my sincere gratitude to senate research committee (SRC) grant of University of Moratuwa, for providing financial assistantship to this research work under the grant number SRC/LT/2013/11.

I thank the management of ATG Gloves (Pvt) Ltd, Lalan Rubbers (Pvt) Ltd and Chemical Industries Colombo Ltd for supplying me the materials required for the project work.

I also like to express my sincere gratitude to Mr. V.S.C. Weragoda, Senior Lecturer, Department of Materials Science and Engineering, for the support given during my research work. In addition to that, I like to express my thanks to all the academic staff members of the Department of Materials Science and Engineering, for their valuable comments.

I would also like to thank Mr. J.M. Unagolla and Mr. K.G.N Thilawala for their support during my research work. Many thanks also go to Dr.(Mrs) M.C.W. Somaratne for her valuable comments and support.

I am grateful to senior technical officer; Mr. S. Chandrapala (retired), technical officers; Mr. M.A.P.C. Gunawardena, Mr. F. Ranasinghe, Mr. S.D. Karunaratna, Mr. R. Karunathilaka, other laboratory staff; Mr. R.R.P. Perera, Mr. W.P.W. Abeyarathne, Mr. H. Amal, office staff and other nonacademic staff members of the Department of Materials Engineering, for their assistance and contribution to my research work.

I would like to thank Mrs. H.B.R. Sajeewani, technical officer, and other laboratory staff of Department of Chemical and Process Engineering, University of Moratuwa for their support.

I greatly acknowledge Dr.(Mrs.) Dilhara Edirisinghe, Head of Rubber Technology and Development Department, Rubber Research Institute, and other staff for providing me the testing facilities in their laboratory.

I would also like to thank Ms. Sanjeewani Jayewardena, Research Engineer, Industrial Technology Institute, for the help given by her for using the testing facilities.

I thank my husband Mr.C.P.Hewakottage and my parents for the assistance and encouragement given by them during this period.

Finally, I would like to express my pardon if I have inadvertently omitted the name of those to whom thanks is due.

L.A.D.A. Liyanaarachchi

## Table of Contents

Declaration .....	i
Abstract .....	ii
Acknowledgment .....	iii
List of Figures .....	viii
List of Tables.....	xi
List of Terms, Abbreviations and Symbols.....	xii
1 INTRODUCTION .....	1
2 LITERATURE REVIEW.....	3
2.1 Synthetic Rubbers.....	3
2.2 Acrylonitrile Butadiene Rubber (NBR) .....	3
2.3 Carboxylated Acrylonitrile Butadiene Rubber (XNBR).....	5
2.4 Filler Materials for Rubber.....	6
2.4.1 Particle shape .....	7
2.4.2 Particle size .....	8
2.4.3 Particle surface area .....	8
2.4.4 Particle surface activity .....	8
2.5 Effect of Fillers on the Properties of Rubber.....	9
2.6 Precipitated Silica.....	10
2.7 Surface Chemistry of Silica.....	10
2.8 Surface Modification of Silica .....	11
2.8.1 Surface modification of silica with coupling agents .....	12
2.9 Reinforcement of Latex .....	13
2.10 Reinforcement of XNBR Latex .....	13
3 EXPERIMENTAL .....	16
3.1 Materials .....	16
3.2 Methods .....	16
3.2.1 Characterization of latex .....	16
3.2.1.1 pH of latex .....	16
3.2.1.2 Dry rubber content of latex.....	16
3.2.2 Preparation of polymers .....	17
3.2.2.1 Characterization of polymers .....	18

3.2.3	Surface modification of silica .....	19
3.2.3.1	Non aqueous medium (NAM) modification.....	19
3.2.3.2	Aqueous medium (AM) modification .....	19
3.2.3.3	Preparation of NAM modified filler dispersions.....	20
3.2.4	Examination of dispersion stability.....	21
3.2.5	Preparation of dispersions and emulsions of compounding ingredients .....	21
3.2.6	Compounding of latex and film casting .....	22
3.2.7	Evaluation of vulcanizate properties.....	25
3.2.7.1	Physical properties .....	25
3.2.7.2	Morphological studies .....	26
3.2.7.3	Swelling properties, crosslinking densities and rubber/filler interactions .....	27
4	RESULTS AND DISCUSSION .....	29
4.1	Characterization of Latex .....	29
4.1.1	pH of latex.....	29
4.1.2	Dry rubber content of latex .....	29
4.2	Characterization of Synthetic Polymers .....	29
4.2.1	FTIR spectra of M <sub>100</sub> , M <sub>80</sub> E <sub>20</sub> and M <sub>60</sub> E <sub>40</sub> polymers .....	29
4.3	Characterization of Modified Silica .....	32
4.3.1	Fourier transform infrared (FTIR) analysis of modified fillers .....	32
4.3.2	Thermogravimetric (TGA) analysis of modified fillers.....	32
4.4	Evaluation of Properties of Films Cast for Preliminary Investigation .....	34
4.4.1	Evaluation of properties of films cast from first batch of latex .....	34
4.4.2	Evaluation of properties of films cast from Method C (Second batch of latex).....	39
4.4.2.1	FTIR analysis of cast films.....	39
4.4.2.2	Physical properties .....	42
4.4.2.3	Morphological studies .....	47
4.4.2.4	Crosslink densities and rubber filler interaction parameter.....	53
5	CONCLUSIONS.....	56
6	Suggestions for Future Work .....	57

7	References .....	58
	<i>[Appendix – I: Publications]</i> .....	60

## List of Figures

Figure 2.1: The polymerization reaction of acrylonitrile and butadiene.....	4
Figure 2.2: Crosslinks of carboxylated acrylonitrile butadiene rubber with zinc oxide .....	6
Figure 2.3: Scanning electron microscopic images of fillers (a) Calcium carbonate – isometric shape (b) Kaolin – platy shape (c) Wollastonite – acicular or needle shape (d) Glass fibre – fibrous shape (e) precipitated silica – Cluster shape .....	7
Figure 2.4: Bonds present on the silica surface .....	11
Figure 2.5: General formula of a silane coupling agent.....	12
Figure 3.1: Diagram of polymerization set up .....	17
Figure 3.2: Process steps of method A1 .....	23
Figure 3.3: Process steps of method A2.....	23
Figure 3.4: Process steps of method B .....	24
Figure 3.5: Process steps of method C .....	24
Figure 3.6: Process steps of method D.....	25
Figure 4.1: FTIR spectra of synthesized polymers .....	29
Figure 4.2: Chemical structure of M <sub>100</sub> polymer .....	30
Figure 4.3: Chemical structure of co-polymers of MAA and EHA .....	30
Figure 4.4: FTIR spectra of M <sub>100</sub> , M <sub>80</sub> E <sub>20</sub> and M <sub>60</sub> E <sub>40</sub> polymers within wave number range of 1660-1760 cm <sup>-1</sup> .....	31
Figure 4.5: FTIR spectra of M <sub>100</sub> , M <sub>80</sub> E <sub>20</sub> and M <sub>60</sub> E <sub>40</sub> polymers within wave number range of 2800-3100 cm <sup>-1</sup> .....	31
Figure 4.6: FTIR spectra of unmodified silica, MF <sub>na</sub> M <sub>80</sub> E <sub>20</sub> and washed MF <sub>na</sub> M <sub>80</sub> E <sub>20</sub> .....	32
Figure 4.7: Variation of ratio of remaining weight/ initial weight of silica, M <sub>80</sub> E <sub>20</sub> , MF <sub>na</sub> M <sub>80</sub> E <sub>20</sub> and washed MF <sub>na</sub> M <sub>80</sub> E <sub>20</sub> .....	33
Figure 4.8: Variation of ratio of remaining weight/ initial weight of silica, M <sub>80</sub> E <sub>20</sub> , MF <sub>na</sub> M <sub>80</sub> E <sub>20</sub> and washed MF <sub>na</sub> M <sub>80</sub> E <sub>20</sub> between 1 to 0.9.....	33
Figure 4.9: The effect of filler loading on the (a) Tensile strength (b) Modulus at 300% elongation, of MF/ UMF added vulcanizates of XNBR films prepared by method A2.....	35



Figure 4.10: Variation of swelling % with filler concentration of films prepared by method A2.....	36
Figure 4.11: Variation of crosslink density with filler concentration of films prepared by method A2.....	36
Figure 4.12: Variation of rubber-filler interaction parameter with filler concentration of films prepared by method A2 .....	37
Figure 4.13: FTIR spectrum of unfilled XNBR cast film .....	40
Figure 4.14: FTIR spectra of unfilled XNBR cast film, unmodified filler filled XNBR cast film and silica filler.....	41
Figure 4.15: The effect of filler loading on the tensile strength of MF/ UMF added vulcanizates of XNBR.....	42
Figure 4.16: The effect of filler loading on the modulus at 300% of MF/ UMF added vulcanizates of XNBR.....	42
Figure 4.17: The effect of filler loading on the elongation at break % of MF/ UMF added vulcanizates of XNBR .....	43
Figure 4.18: The effect of filler loading on the tear strength of MF/ UMF added vulcanizates of XNBR.....	46
Figure 4.19: Microstructures of tensile fracture surfaces of unfilled XNBR vulcanizates at magnifications of 50, 100 and 200 .....	48
Figure 4.20: Microstructures of tensile fracture surfaces of UMF filled XNBR vulcanizates at magnifications of 50, 100 and 200 .....	48
Figure 4.21: Microstructures of tensile fracture surfaces of MF <sub>a</sub> M <sub>100</sub> filled XNBR vulcanizates at magnifications of 50, 100 and 200 .....	48
Figure 4.22: Microstructures of tensile fracture surfaces of MF <sub>a</sub> M <sub>80</sub> E <sub>20</sub> filled XNBR vulcanizates at magnifications of 50, 100 and 200 .....	49
Figure 4.23: Microstructures of tensile fracture surfaces of MF <sub>a</sub> M <sub>60</sub> E <sub>40</sub> filled XNBR vulcanizates at magnifications of 50, 100 and 200 .....	49
Figure 4.24: Microstructure of cross section of unfilled vulcanizate.....	50
Figure 4.25: Microstructure of cross section of vulcanizate filled with UMF.....	51
Figure 4.26: Microstructure of cross section of vulcanizate filled with MF <sub>a</sub> M <sub>100</sub> .....	51
Figure 4.27: Microstructures of cross sections of vulcanizate filled with MF <sub>a</sub> M <sub>80</sub> E <sub>20</sub> .....	52

Figure 4.28: Microstructures of cross sections of vulcanizate filled with MF <sub>a</sub> M <sub>60</sub> E <sub>40</sub> .....	52
Figure 4.29: The effect of filler loading on swelling % of MF/ UMF added vulcanizates .....	53
Figure 4.30: The effect of filler loading on crosslink density of MF/ UMF added vulcanizates .....	53
Figure 4.31: The effect of filler loading on rubber-filler interaction parameter of MF/ UMF added vulcanizates .....	54

## List of Tables

Table 3.1: Identification codes of polymers.....	18
Table 3.2: Formulations for preparation of AM modified and unmodified filler dispersions.....	20
Table 3.3: Formulations used for the preparation of NAM modified filler dispersions .....	20
Table 3.4: Formulation used in preparing 33% (w/w) ZnO dispersion .....	21
Table 3.5: Formulation used in preparing 25% (w/w) ZDEC dispersion .....	21
Table 3.6: Formulation used in preparing styrenated phenol emulsion.....	22
Table 3.7: Formula used for compounding of XNBR latex.....	22
Table 4.1: Tensile strength, modulus at 300% elongation and elongation at break (%) of the unfilled, UMF filled and MF <sub>na</sub> M <sub>100</sub> filled films .....	34
Table 4.2: Tensile strength of UMF and MF <sub>na</sub> M <sub>100</sub> filled films prepared according to method B .....	38
Table 4.3: Tensile properties of UMF and MF <sub>a</sub> M <sub>100</sub> filled films prepared according to method C .....	38
Table 4.4: FTIR peaks of unfilled XNBR cast film and corresponding vibrations ...	40
Table 4.5: Increase of tensile strength of 15 phr filled vulcanizates over unfilled vulcanizate.....	44
Table 4.6: Increase of tensile strength of 15 phr modified filler (MF) filled vulcanizates over unmodified filler (UMF) filled vulcanizate.....	44
Table 4.7: Increase of moduli of 15 phr filled vulcanizates over unfilled vulcanizate .....	45
Table 4.8: Increase of tear strength of 20 phr filled vulcanizates over unfilled vulcanizate.....	47

## **List of Terms, Abbreviations and Symbols**

AM	Aqueous medium
BCW	Bacterial cellulose whisker
CB	Carbon black
CN	Polar nitrile group
COOH	Carboxylic group
EHA	2-ethylhexyl acrylate
FTIR	Fourier Transform Infrared Spectroscopy
KOH	Potassium hydroxide
MAA	Methacrylic acid
MF	Modified filler
MWCNT	Multiwalled carbon nanotube
NAM	Non aqueous medium
NBR	Acrylonitrile butadiene rubber
PVC	Polyvinyl chloride
SDBS	Sodium dodecyl benzene sulphonate
SEM	Scanning electron microscopy
SP	Synthetic polymer
TGA	Thermogravimetry Analysis
THF	Tetrahydrofuran
UMF	Unmodified filler
w/w	Weight/Weight
XNBR	Carboxylated acrylonitrile butadiene rubber

ZDEC	Zinc diethyldithiocarbamate
ZnO	Zinc oxide