


UP/1004/23/07

9



# INVESTIGATION OF AN APPROPRIATE METHODOLOGY FOR PRESERVATION OF TRADITIONAL SRI LANKAN MURAL PAINTINGS

LIBRARY  
UNIVERSITY OF MORATUWA, SRI LANKA  
MORATUWA



University of Moratuwa, Sri Lanka  
Electronic Theses & Dissertations  
www.lib.mrt.ac.lk

THANTHREGE DONALD NISHANTHA PERERA

72<sup>06</sup>  
72(043)

JULY 2006

University of Moratuwa



87269

87269

A THESIS SUBMITTED TO THE UNIVERSITY OF MORATUWA FOR  
ASSESSMENT FOR THE DEGREE OF DOCTOR OF PHILOSOPHY IN  
ARCHITECTURAL CONSERVATION OF MONUMENTS AND SITES, UNDER  
A GRANT GIVEN BY THE SENATE RESEARCH COMMITTEE OF THE  
UNIVERSITY

87269

INVESTIGATION OF  
AN APPROPRIATE METHODOLOGY  
FOR PRESERVATION OF TRADITIONAL  
SRI LANKAN MURAL PAINTINGS



University of Moratuwa, Sri Lanka.  
Electronic Theses & Dissertations  
[www.lib.mrt.ac.lk](http://www.lib.mrt.ac.lk)

Content of the thesis: Testing of validity and applicability of the hypothesis  
*'it is possible to reduce the rate of decay of mural paintings and probability of  
generation of defects in them by controlling their behavior'*

T.D.N. PERERA  
DEPARTMENT OF ARCHITECTURE,  
UNIVERSITY OF MORATUWA, SRI LANKA.

JULY 2006

## DECLARATION

I do hereby declare that the material present in this thesis was resulted from research exclusively carried out by me under the supervision of Prof. T.K.N.P. De Silva. The thesis contains the results of my own independent research except where due references have been made. Persons who provided technical assistance for my research work are duly acknowledged. This thesis has not been previously or concurrently submitted in whole or part to any university or institution for the same or any other degree.

### *UOM Verified Signature*

T.D.N. Perera,  
Candidate

Date: Sep. 23, 2005

I certify that the work reported in this thesis was carried out by the candidate, is of suitable standard for the degree for which it was submitted and worth of consideration.



University of Moratuwa, Sri Lanka.  
Electronic Theses & Dissertations

### *UOM Verified Signature*

  
Prof. T.K. Nimal P. De Silva,  
Supervisor

Date:

## Publications by T.D.N. Perera relevant to the thesis

1. 2003, 'Architectural conservation of traditional mural paintings: the Sri Lankan experience', *Built environment Sri Lanka*, 4, 1, pp. 13-19
2. 2004, 'A non-destructive method to measure the rate of decay of mural paintings', *Built environment Sri Lanka*, 4, 2, pp. 55-58

## Abstracts

1. 2002, 'A simulated study on the correlation between stable behavior and the rate of decay in traditional Sri Lankan mural paintings', *SLAAS Proceedings part 1 (abstracts)*, p. 92
2. 2002, 'An investigation of the usage of traditional material to preserve traditional Sri Lankan mural paintings', *SLAAS Proceedings part 1 (abstracts)*, p. 93
3. 2002, 'The identification of traditional Sri Lankan painting techniques', *SLAAS Proceedings part 1 (abstracts)*, p. 94
4. 2002, 'The investigation of behavior patterns in traditional Sri Lankan mural paintings', *SLAAS Proceedings part 1 (abstracts)*, p. 95
5. 2003, 'Determination of degree of effectiveness of repair intervention on the simulated samples of traditional Sri Lankan mural paintings using an indirect method of measurement of rate of decay', *SLAAS Proceedings part 1 (abstracts)*, p. 127
6. 2003, 'Measurement of behavior of traditional mural paintings in relation to its principal actions', *SLAAS Proceedings part 1 (abstracts)*, p. 128
7. 2004, 'Identification of gamboge used in traditional mural paintings with special reference to implications of its decay', *Chemistry in Sri Lanka*, 21, 2, pp. 24-25
8. 2004, 'Preservation of southern paintings deteriorated by formation of subflorescence', *SLAAS Proceedings part 1 (abstracts)*, p. 129
9. 2005, 'A methodology for preservation of traditional Sri Lankan mural paintings', *SLAAS Proceedings part 1 (abstracts)*, p. 127
10. 2005, 'Impact of decay on the structure and behavior of traditional mural paintings', *SLAAS Proceedings part 1 (abstracts)*, p. 33



University of Moratuwa, Sri Lanka  
Electronic Theses & Dissertations  
[www.etd.mrt.ac.lk](http://www.etd.mrt.ac.lk)

## ABSTRACT

This research was founded with an objective of finding the most effective method of preservation of traditional Sri Lankan mural paintings. Investigation was separated into three main areas. These are determination of necessary actions in preservation, investigation of preservation mechanisms and investigation of applicability of these methods. Actions needed in preservation were identified by analyzing present condition of paintings. Paintings were classified into several logical groups to facilitate analysis. A criterion for classification was developed considering all possible factors of sorting. Classification of paintings according to the period of production was the most appropriate criterion since this automatically classified paintings on technique, school, climate, pattern of decay, pattern of deterioration and the degree of deterioration. Analysis of condition of paintings disclosed following facts:

1. all paintings are in a rapid rate of decay
2. deterioration is a result of natural decay and accelerated decay due to dilapidation
3. intervention based on synthetic resins prevented fragmentation and loss of material but accelerated the rate of decay

This information led to the decision that adequate repair and prevention of deterioration would be the most needed actions in conserving Sri Lankan paintings. Analyzes of these facts emphasized that there was a definite need to develop a viable method of reduction of the rate of decay of paintings. Development of the most appropriate method needed following background information: principles of traditional technology; social aspects that led to creation, usage and maintenance of paintings and traditional methods of conservation and maintenance. There were few direct and indirect sources to gather this information. These were traditional technical texts, historic records, legend memory and information generated from physical and chemical analyses. Present social conditions that led to survival and destruction of paintings were also analyzed. Technical analyses were based on structure, composition and behavior of Sri Lankan paintings and survival and performance of different types of paintings in different climatic zones. Most appropriate chemical and physical analytical methods were used in the analysis.

Constant nature of structure, composition, production process and procedure of painting in paintings belonging to a particular class and analogy among different classes indicated strict adherence of production techniques to rules and regulations of traditional technology. Seven major Sri Lankan painting techniques were identified. Classical, medieval and southern are the dominant techniques among them. The most major difference among these techniques is the structure and composition of ground. Two major techniques were therefore defined based on the usage of the process of carbonation in the ground. The characteristic feature of Sri Lankan painting techniques is the use of biotechnology.

A heavy amount of microbiological actions and enzymatic reactions had been used to attain key properties not gained by other means. Use of most stable material is a law of traditional technology. Certain principles of traditional technology that realized appropriate coordination between paintings and environment were identified. A particular traditional painting technique fulfilled the needs of the corresponding painting school and users of paintings produced by that technique. Usage and maintenance also followed definite rules, regulations and guidelines. These were identified by analyzing later modifications to paintings.

Special attention was given to understand actions occurring in paintings. These actions were identified as interactions of paintings with the environment. Interactions with environment and response of paintings to these interactions were defined as behavior. Water transmission and thermal movement of paintings were identified as main actions of behavior. These dynamic physical actions bear on most other physical, chemical and microbiological actions. Paintings on masonry and wood support absorb water through support, transmit towards the surface and evaporate on the surface. Paintings on rock support absorb water through the surface and disperse throughout the ground. Porosity of ground and permeability of paint layer are important parameters in both of these absorption types.

Most actions occurring in paintings are detrimental to them and called actions of decay. Few favorable actions called actions of preservation were also identified. Various factors become favorable or detrimental in specific ranges and combinations with other factors. Decay is a continuous process associated with every painting. Decay results in a change of material, material properties and structure. These changes bring about deterioration, i.e. formation of defects. The rate of decay accelerates with the formation of defects. Behavior of every painting becomes destructive with the formation of defects.

Prevention of decay is the principle action necessary in preserving paintings. This is the key task necessary to preserve deteriorated traditional mural paintings. Prevention of fragmentation and loss of material are other important needs. This investigation was centered on determination of the most effective method of minimizing the rate of decay. Simulated samples of paintings were used in the investigation. Production processes of these simulated samples were determined using information obtained from traditional technical texts and chemical and physical analyses of samples of paintings. It was found that two types of samples could represent all Sri Lankan paintings. These are samples with lime ground and samples with clay ground. It was decided to produce samples at four categories of increasing complexity to reduce errors during analysis. Elementary samples simulated the painting ground, basic samples simulated the multilayered structure of paintings and advanced samples simulated complex structure of paintings. Advanced samples had heterogeneous paint layers and complex ground.

Representative samples represented the actual paintings. Enzymatic and microbiological actions mentioned in traditional technical texts were used to produce representative samples.

This investigation needed methods to measure behavior and the rate of decay. Behavior could be adequately measured using parameters of main actions of behavior. An indirect method based on intensity of defects and difference in hue was used to measure relative rates of decay. Methods of reduction of rate of decay tested were removal of factors of decay, environmental control, repair of defects, induction of equilibrium behavior and few specific actions of preservation. These different methods were successful at various degrees. Removal of some factors of decay reduced the rate of decay at all instances. However, it had a limited amount of success due to the fact that total removal of some factors like water and thermal energy increased decay. Environmental control remarkably reduced the rate of decay. However, this did not guarantee the long-term existence of paintings. Furthermore it was difficult to adopt. Natural actions of preservation takes very long durations and difficult to manage. Maintaining conditions that enhancing these actions was the only external intervention possible. Further analysis of these methods of reduction of rate of decay disclosed the fact that all of these mechanisms were effective when they induce equilibrium. Special attention was therefore given to test possibility of reducing the rate of decay by inducing equilibrium behavior. Existence of a relationship between the degree of equilibrium and the rate of decay was the main hypothesis tested in this research.



University of Moratuwa, Sri Lanka  
Electronic Theses & Dissertations  
www.lib.moratuwa.lk

Relationship of equilibrium behavior and the rate of decay was studied at four levels using four categories of samples. A completely randomized design was used. Relationship between behavior and the rate of decay was tested with elementary, basic and advanced samples. Behavior was changed by altering input physical factors. A distinct relationship was observed. Relationship of degree of equilibrium with the rate of decay was also investigated with these samples. Equilibrium was quantitatively changed by allowing the samples to absorb moisture at different known rates under different known temperatures and relative humidity. A definite correlation existed. These relationships were significant ( $p < 0.5$ ) or highly significant ( $p < 0.1$ ) in each category of all types of samples. Definite relationship existed between the degree of equilibrium in behavior and rate of decay of traditional paintings was established with a high confidence level. It was found that the degree of deviation from the optimal equilibrium is the factor that determined the rate of decay. Further analysis done with representative samples disclosed the fact that each painting technique has a set of optimal ranges of equilibrium. There is an optimal point of equilibrium for each action and optimal range of overall equilibrium in each class of painting. This optimal level could be defined in terms of input parameters. Optimal level of equilibrium for each technique of painting could therefore be determined.

Equilibrium reduced the probability of generation of defects. Equilibrium at optimal level reduced the rate of decay too. Analysis of mechanisms of reduction of rate of decay disclosed the fact that all methods of reducing the rate of decay minimize decay by inducing equilibrium. It was therefore emphasized that induction of equilibrium at the optimal level is the most effective method available to reduce the rate of decay of mural paintings. Mechanism of reduction of rate of decay by induction of equilibrium behavior was investigated using simulated samples. Paintings in equilibrium maintained all factors at their moderate rates. These intermediate levels approached optimal levels of most actions. Equilibrium brought about proper coordination between all actions. It did not allow any action to grow beyond the favorable limit. It reduced tear and wear. It tremendously decreased the probability of formation of defects. These factors are important to all paintings.

Method of inducing equilibrium behavior at the most optimum level is called stabilization. Possibility of practical induction of stabilization was tested on simulated samples. All possible methods of stabilization were investigated. These are repair of defects, environmental control and application of controlled amounts of input factors. All ancient paintings have defects as a part and parcel of their structure. Adequate repair of these defects is compulsory. Special emphasis is therefore given to test possibility of stabilization by repair of defects. Samples were subjected to destructive intervention to generate defects. Their behavior was measured and compared with normal samples. Repair was done with traditional material and synthetic material. Quality of repair done with synthetic material was better than traditional material. Quality of repair with traditional material was also at an acceptable level. Repair with synthetic material however deviated behavior away from equilibrium. Repair with traditional material was effective in bringing equilibrium closer to the original level.

It was therefore decided that repair of defects with traditional material could reduce the rate of decay of traditional mural paintings. Possibility of practical adoption of the method was also investigated in five selected sites. Necessary actual measurements were done; conservation plans were developed. It was found from this study that repair of paintings with traditional material and maintaining their environment within acceptable ranges were adequate for stabilization. Elaborate measurements were not necessary to adopt the stabilization method. It was established that the stabilization method can be adopted as a systematic process of reduction of rate of decay and decreasing the probability of emergence of defects.

## **PREFACE**

The objective of performing research in the field of painting conservation is the desire to study natural actions without set artificial boundaries within different fields. Painting conservation is the field where researchers enjoy the freedom of performing research without restrictions under a defined field. This essentially demands and promotes a multidisciplinary approach. Research in painting conservation is however a challenging task. Complex nature of paintings brings about a vast number of interrelated actions that analysis becomes difficult. This research is primarily concerned with the actions necessary to arrest the natural action of decay. Analysis of complex behavior, decay and deterioration as a singular sequential process was the mechanism used in this research. The study concentrates on nullification of decay actions by the coordinated functioning of paintings with their respective environments.

Preservation is the most essential attribute in architectural conservation and hence in conservation research. This study primarily investigates traditional Sri Lankan mural paintings and their preservation methods. Principles of traditional technology applied during production of paintings, usage and maintenance are taken as the basis for the development of viable preservation methods. Preservation methods are analyzed in relation to the interaction of paintings with their environment. It was understood that conservation measures perfectly suited for modern paintings destruct traditional paintings. This is a result of difference in mode of interaction of these paintings with the environment. Root of the problem existing within present methods of conservation lies on this factor. Preservation method developed in this research took this fact into account.

Main obstacle met in this research was the random nature of variables encountered. Inherent random nature is a result of various combinations of factors involved. A similar problem exists in biology and medicine. Biostatistics is used in research in these fields. A similar approach was used in this research. Limitation of intervention on genuine paintings to a minimum was a major objective in this study. Simulated samples were used to realize this goal. These samples provided the additional benefit that tests could not be carried out on genuine paintings could be performed on them. Special attention was taken to produce samples that accurately simulated genuine paintings. All techniques of traditional mural paintings are included in the study. Attributes common to all these paintings and contrasting features could therefore be identified.

Content of the thesis is original materials generated from laboratory and field investigations. Sources of information gathered from literature survey are duly acknowledged. Analytical research was carried out at the ACOMAS Laboratory of the Department of Architecture and the Microscopy Laboratory at the Department of Materials Engineering. Sites where investigations were done are mentioned in the thesis.

## ACKNOWLEDGEMENT

Performing research at the highest level is the best achievement of any researcher. It would have been very difficult to realize this goal and accomplish the set target with an appropriate standard without the help of many distinguished personnel. It is my responsibility to introduce them to the academic community for the benefit of all researchers in the field.

My supervisor Prof. T.K.N.P. De Silva is the pioneer of the project who had taken every effort to ensure its successful completion. This eminent professor had given me necessary academic guidance not only as the most senior academic in the island in this field but also as a world renowned authority in painting conservation. He supervised me effectively throughout my research project as the senior-most professor in the Department of Architecture. He handled all official matters of the project efficiently in the capacity of Dean, Faculty of Architecture. He had taken efforts to find financial assistance required for the project. I thank him gratefully as the academic who supervised me, helped me most throughout the project and pioneered the establishment of the ACOMAS Course in the Department of Architecture and ensured its successful functioning.

Archt. C.J. de Saram, Course Director, ACOMAS, had taken every effort and given me help in successful completion of the project in the required standard. He had repeatedly given me necessary advice to maintain the essential quality and standard of research and publications. He had given attention to read and correct my thesis and research papers. He helped me in the capacity of very senior academic in the department. He helped me to solve many official matters in the capacity of the Course Director of ACOMAS course. I thank him with the highest dignity.

This doctoral course is a new program in the Department of Architecture. The Board of Higher Degrees (BHD) of the Faculty of Architecture was set up at the time of initiation of this course. Prof. L. Alwis, Emeritus Professor, University of Moratuwa; Dr. R. Dayarathna; Dr. L.S.R. Perera and Dr. M.P.R. Emmanuel had given me all advice and guidance necessary for the matters pertaining to my registration for the course. Prof. L. Balasuriya, former Dean, Faculty of Architecture, members of BHD and Prof. N. Rathnayake, Director of Postgraduate Studies, Faculty of Engineering had also given me valuable advice in this regard.

Enormous efforts have been taken by Prof. B.L. Tennekoon, former Chairman, Senate Research Committee (SRC) and Dr. L.S.R. Perera to obtain financial assistance for the project. The present Chairman of SRC, Prof. S.R. de S. Chandrakeerthi and all members of Senate Research Committee also had given me invaluable help. I must thank the SRC of the University of Moratuwa for providing financial assistance for the course.

Ford Foundation, USA and J. Paul Getty Foundation, USA had given additional support. I offer my grateful thanks to all of these prestigious institutions.

Help of senior academics in many fields were necessary for the course. Academic guidance was given by many eminent academics of the subject. Prof. M.S. Manawadu of Department of Architecture had given me all the advice necessary to perform research under doctoral methodology and prepare the thesis under recognized criterion. Dr. N.A. Wickramasinghe, Director General, National Museums, had given me valuable advice on chemical methods used in painting conservation. Mr. Jagath Weerasinghe, Senior Lecturer, Post Graduate Institute of Archaeology, University of Kelaniya, guided me introducing necessary areas of research in painting conservation. Dr. B.D. Nandadeva had given guidance on research in painting conservation.

I must thank Dr. M.P.R. Emmanuel for giving me initial advice in preparing research papers and continuously encouraging me to publish my research work. Dr. W.K. Hirimburegama has kindly indicated me statistical errors in my research work. Invaluable advice in research and publication was given by Dr. L.A. Samayawardena. He had taken tremendous efforts in reading and correcting my thesis while doing post doctoral research at the Queens University, Canada. Dr. K.D. Silva had given me invaluable advice while doing his doctoral course at the University of Wisconsin, Milwaukee.

Dr. C.S. Wettasinghe, Director of National Archives provided me with a valuable database of IR spectroscopic analysis. Academic help was given by Mr. S. Weerawarnakula, Senior Lecturer, Department of Earth Resource Engineering of University of Moratuwa; Ms. R.C. Kodikara, Librarian, University of Moratuwa; Archt. S.K. Ranasinghe; Eng. A.D.G. Maduka and Mr. R.K.S. Fernando. Several local and foreign scholars were in contact with me giving valuable help, advice and directions. They exposed sources of material relevant to my research and helped me in interpreting Sanskrit terms of traditional recipes.

Technical help was given by Mr. V.P.A. de Mel, Technical Officer, ACOMAS Laboratory; Mr. S.G. Weerasooriya, retired Senior Technical Officer, Department of Architecture; Mr. S. Chandrapala, Staff Technical Officer, Department of Materials Engineering and Mr. G.P. Perera, Staff Technical Officer, Department of Earth Resource Engineering. Mr. V.P.A. de Mel assisted me in chemical analysis and preparation of samples of paintings. He assisted me continuously on many academic and official issues taking utmost care, interest and attention. Mr. R.A.J. Kithsiri, Technical Officer of the Faculty of Architecture had given invaluable help continuously. Mr. & Mrs. S.G. Weerasooriya also helped me in many occasions. Mr. A.H. Witharana, Mr. A. Colombage, Mr. D. Wagachchi and Mr. A. Jayasundara, conservators of the Central Cultural Fund, provided me information and given me training on practical methods of conservation.

Miss. C.K.A.S. Yapa and Miss. K.A. Indirani had spent several days in many sites in assisting me in detailed documentation of defects. Assistance was given in photographic documentation by Mr. S.S. Alahakoon, Technical Officer, Department of Architecture and Mr. A.M.S. Attanayake, Technical Officer, Faculty of Architecture. Miss. C.K.A.S. Yapa provided me valuable samples of paintings of several rare sites. Mr. W.D. Gnanasiri and Mr. A.A.A. Perera provided me samples of traditional material.

Many other resource personnel, attached to several local and foreign universities and institutions and too numerous to mention, helped me in various means. I must thank them all. I convey my grateful thanks to everyone who helped me in bringing this project a successful one.



University of Moratuwa, Sri Lanka  
Electronic Theses & Dissertations  
[www.lib.mrt.ac.lk](http://www.lib.mrt.ac.lk)



# CONTENTS

	Page No.
Abstract	1
Preface	5
Acknowledgement	6
Contents	9
List of Tables	12
List of Figures	14
Chapter Breakdown	17
Introduction	19
<b>Chapter One: The present context of traditional mural paintings</b>	<b>23</b>
1.1 Characteristic features of the mural painting tradition	23
1.2 Occurrence of mural paintings	36
1.3 Present usage, conservation and maintenance practice	44
1.4 Survival of paintings under undisturbed condition	50
1.5 Survival under disturbed condition	53
1.6 Remains of a rich tradition	58
1.7 Criterion necessary to preserve mural paintings	70
1.8 References	78
<b>Chapter Two: The structure, behavior, decay and conservation of mural paintings</b>	<b>82</b>
2.1 Composition of mural paintings	82
2.2 Structure of mural paintings	88
2.3 The traditional Sri Lankan painting techniques and production processes	91
2.4 Behavior, decay and mechanisms of decay	97
2.5 Research in preservation	111
2.6 Conservation strategies	114
2.7 Conservation intervention	117
2.8 Methods used in conservation analyses	128
2.9 References	134
<b>Chapter Three: Preservation of decaying paintings</b>	<b>142</b>
3.1 Investigation of paintings, their decay and survival	142
3.2 Behavior of mural paintings	151
3.3 Decay of mural paintings	170
3.4 Mechanism of survival of mural paintings	196
3.5 The appropriate preservation methodology	206
3.6 Method of investigation	213
3.7 References	217

<b>Chapter Four: Investigation of methods of reduction of rate of decay</b>	<b>218</b>
4.1 Method of investigation	218
4.2 Parameters of behavior and methods of measurement of behavior	237
4.3 Measurement of rate of decay	248
4.4 Investigation of preservation mechanisms	265
4.5 Paintings in equilibrium behavior	294
4.6 References	306
<b>Chapter Five: Investigation of methods of intervention to stabilize behavior of mural paintings</b>	<b>308</b>
5.1 The investigation procedure	308
5.2 State of equilibrium in paintings with defects	311
5.3 The appropriate point of equilibrium	320
5.4 Intervention to stabilize behavior	327
5.5 Nature, behavior and rate of decay of paintings under stabilization intervention	358
5.6 References	361
<b>Chapter six: Investigation of applicability of stabilization: case studies</b>	<b>362</b>
6.1 Objectives and methodology	362
6.2 Selection of sites	365
6.3 Vessagiriya cave, Anuradhapura	366
6.4 Tivanka image house, Polonnaruva	373
6.5 Dome of Gadaladeniya image house, Pilimatalawa	380
6.6 Degaldoruva rock temple	387
6.7 Shailabimbaramaya, Dodanduwa	393
6.8 Additional on site investigations	397
6.9 Analysis of sites where paintings are disintegrated	405
6.10 General observations and conclusions	409
6.11 References	416
<b>Chapter Seven: Systematic conservation of mural paintings</b>	<b>418</b>
7.1 The adoptable conservation process	418
7.2 The process of systematic conservation	428
7.3 Conservation of Sri Lankan mural paintings	450
7.4 Stabilization and preservation	453
7.5 References	458
Conclusion	459
Bibliography	466

Appendix One: The environmental chamber	489
Appendix Two: Microchemical analyses	490
Appendix Three: The program used to measure color difference	493



University of Moratuwa, Sri Lanka.  
Electronic Theses & Dissertations  
[www.lib.mrt.ac.lk](http://www.lib.mrt.ac.lk)

## LIST OF TABLES

	Page No.
1.1 Classification of paintings	63
1.2 Attributes of paintings in different classes	64
1.3 Results of intervention of paintings	67
2.1 Material present in Sri Lankan paintings	85
2.2 Composition of traditional paintings	86
2.3 Composition of ground and paint-receiving layer	87
2.4 Material used to produce paint	87
2.5 Composition of Sri Lankan paintings	87
2.6 Structure of Sri Lankan paintings	89
2.7 Stratified structure of Sri Lankan paintings	89
2.8 Structure of medieval and southern paintings	88
2.9 Plant material mentioned in traditional Sri Lankan technical texts	94
3.1 Conditions observed in painting samples	160
3.2 Effects of processes of decay	179
3.3 Decay products identified	188
3.4 Conditions under which paintings survived	197
4.1 Species selected to test antioxidant activity	223
4.2 Suitability of samples	226
4.3 Variance in dimensions	226
4.4 Parameters of behavior of samples	226
4.5 Degrees of significance between factors of behavior in advanced samples	242
4.6 Variation of significance at different rates of moisture and temperature	243
4.7 Factors of correlation in different relationships	245
4.8 Material properties of samples	262
4.9 Amount of decay under different conditions	266
4.10 Methods of repair intervention	270
4.11 Intervention on representative samples	288
4.12 Variation of optimal equilibrium conditions in different paintings	291
4.13 Intervention on deteriorated samples	291
4.14 Appropriate equilibrium in different paintings	292
5.1 Categories of samples used for testing	314
5.2 Optimal conditions of equilibrium	325

5.3	Selected temperature-relative humidity factors	325
5.4	Equilibrium attained by environmental control	329
5.5	Attaining equilibrium by environmental control	330
5.6	Effectiveness of repair intervention	337
5.7	Stability of samples	338
5.8	Results of intervention	338
5.9	Ions absorbed to the gel	343
5.10	Plants selected to obtain sap	345
5.11	Relative amount of water transmission	349
5.12	Success of repair methods	355
5.13	Success of repair	356
5.14	Percentage equilibrium induced by each repair intervention	357
6.1	Sites selected for investigation	366
6.2	Analysis of microorganisms at Lankatilaka	406



University of Moratuwa, Sri Lanka  
Electronic Theses & Dissertations  
[www.lib.mrt.ac.lk](http://www.lib.mrt.ac.lk)

## LIST OF FIGURES

	<b>Page</b>
1.1 Usage of color in medieval paintings at Degaldoruva	27
1.2 Neolithic drawings at Manda-galge	38
1.3 Ancient paintings at Varana	39
1.4 Classical image house	41
1.5 Paintings at Lankatilaka image house	51
1.6 Surface moisture levels at Gadaladeniya	56
1.7 Categories of paintings in Sri Lanka	63
1.8 Problems present in paintings at Degaldoruva	65
1.9 A painting at Jinanandaramaya deteriorated due to salt action	66
3.1 Acrylic support used in painting samples	150
3.2 Rates of water transmission and absorption in a lime sample	156
3.3 Moisture absorption from air	157
3.4 Movement of surface at different levels of temperature and moisture	176
3.5 The rate of decay curve of an artificially aged sample	185
3.6 An electron micrograph of Tivanka painting ground	187
3.7 Surface defects in an advanced sample	187
3.8 The process of formation of defects	192
3.9 Deterioration resulted from decay	193
4.1 Antioxidant activity of plant material	223
4.2 A basic sample with clay ground	228
4.3 A basic sample with lime ground	229
4.4 Advanced samples with clay ground	230
4.5 A representative sample of Vessagiriya	233
4.6 A representative sample of Degaldoruva	235
4.7 Relationship of physical factors with surface movement in different samples	244
4.8 Variation of parameters with moisture absorption for category one samples	246
4.9 Relationship of behavior with temperature	247
4.10 Selected IR peak of gamboge	250
4.11 Rate of decay of gamboge	251
4.12 Selected IR peaks of wood-apple gum	252
4.13 Rate of decay of wood-apple gum	252
4.14 Rate of decay of red-ochre	253
4.15 XRD spectrum of Dambulla II ground	254
4.16 XRD spectrum of Gadaladeniya ground	254

4.17	Deformation in an advanced sample	254
4.18	Electron micrograph of the Degaldoruva ground	256
4.19	Measurement of decay using material properties in lime samples	257
4.20	Rate of decay given by defects	259
4.21	Direct and indirect composite decay curves	262
4.22	Range of interpretation of a factor	264
4.23	Rates of decay of representative samples	267
4.24	Degree of significance in factors of decay	269
4.25	Degree of success in repair	271
4.26	Relative rates of decay of repaired samples	271
4.27	Behavior of samples in relation to moisture transmission	272
4.28	Film formation in wood-apple gum	274
4.29	Samples used to test fixation	275
4.30	Impact strength of fixed samples	275
4.31	Variation of decay of samples with absorbed moisture	277
4.32	Variation of decay of samples absorbed heat	278
4.33	Relationship of state of behavior with rate of decay	279
4.34	Variation of rate of decay with degree of equilibrium	283
4.35	Relationship of rate of decay with degree of equilibrium	283
4.36	Variation of rate of decay with degree of equilibrium in paintings	284
4.37	Variation of rate of decay with degree of equilibrium in stratified structures	285
4.38	Variation of rate of decay with degree of equilibrium in complex paintings	286
4.39	Relationship of rate of decay with degree of equilibrium in complex paintings	287
4.40	Rates of decay in representative samples	289
4.41	Generic decay-equilibrium curve that indicates the optimal point	289
4.42	Variation of equilibrium with deterioration	290
4.43	The equilibrium-decay curve	292
4.44	Relative viability of each method	294
4.45	Equilibrium in different paintings	297
4.46	States of equilibrium	298
4.47	Rate of decay in gamboge paint	302
5.1	Samples underwent destructive intervention	311
5.2	Change in strength with defects	313
5.3	Change in equilibrium with defects	314
5.4	Equilibrium change induced by defects	315

5.5	Relative behavior change induced by defects	315
5.6	A deteriorated painting sample	316
5.7	Deterioration under different degrees of equilibrium	321
5.8	Variation of rate of decay with equilibrium	321
5.9	Variation of rate of decay with point of equilibrium	321
5.10	Deterioration under different points of equilibrium	322
5.11	The feasibility curve	322
5.12	Decay of samples under equilibrium	324
5.13	Stability gained after the removal of factors of decay	331
5.14	Result of intervention on behavior and decay	339
5.15	Relationship of surface movement with degree of equilibrium	340
5.16	Salt crystallization in agar agar	344
5.17	Moisture transmission in repaired clay samples	353
5.18	Effectiveness of repair intervention	357
6.1	Areas having different stability at Vessagiriya	370
6.2	Areas separated on behavior change at Vessagiriya	372
6.3	Micro organisms present at Tivanka	376
6.4	Area of investigation at Tivanka	379
6.5	Structure of Dome paintings at Gadaladeniya	380
6.6	Surface imperfections in Gadaladeniya paintings	382
6.7	Destruction of Gadaladeniya paintings by micro organisms	383
6.8	Areas separated on required intervention at Gadaladeniya	386
6.9	A diagrammatic plan of Degaldoruva cave indicating the path of water flow	389
6.10	Investigation of Degaldoruva paintings	392
6.11	Investigation of Shailabimbaramaya paintings	395
6.12	Distribution of surface moisture at Shailabimbaramaya	396
6.13	A painting at Gotabaya Temple	402
6.14	Distribution of moisture at Bellanwila image house	403
6.15	Salts deposited at Bellanwila Image House	404
7.1	Paintings with different levels of deterioration	424
7.2	Paintings belonging to different techniques with different levels of deterioration	424
7.3	Immediate effect of repair on behavior of painting samples	446
7.4	Immediate change in surface moisture after repairing internal voids	447
A1.1	The environmental chamber with connected accessories	489
A3.1	GUI of the ColorCal program	493
A3.2	GUI showing the result dialog box	493

## CHAPTER BREAKDOWN

This thesis consists of seven chapters. Content in each chapter is given below.

### Chapter One: The present context of traditional mural paintings

The first chapter contains the results of a preliminary analytical study of the remaining traditional Sri Lankan mural paintings done with an objective of identifying the research problem. Empirical information obtained is presented under characteristic features of mural painting tradition, conservation and maintenance practices adopted during different eras, results of these actions, present condition of paintings, survival and necessary research in preservation. It finally deals with the necessary areas of research.

### Chapter Two: The structure, behavior, decay and conservation of mural paintings

The second chapter contains information obtained from a survey done to identify methods available to solve problems mentioned in chapter one or to develop such methods. This information is categorized under structure and composition of paintings, mechanisms of decay, methods of conservation intervention, results of intervention and methods used in conservation analysis.

### Chapter Three: Preservation of decaying paintings

An accurate understanding of interaction of mural paintings with their environment was the initial task necessary in this research. This chapter contains methods used in such analysis, results and inferences realized. Content of the chapter is categorized under actions of behavior; processes of behavior; decay; patterns of behavior, decay and deterioration and mechanisms of survival. It finally deals with the methods of solving the research question. The method of investigation and experimental design are included in this description.

### Chapter Four: Investigation of methods of reduction of rate of decay

This chapter describes the research methodology used in testing of hypothesis, results obtained from this investigation, inferences and conclusions realized. Information present in the chapter is divided into following areas: production of simulated samples, methods used in the measurement of behavior and decay and testing of mechanisms of reduction of decay. The chapter finally deals with the most effective method identified.

### Chapter Five: Investigation of methods of intervention to stabilize behavior of mural paintings

This chapter contains information on the investigations carried out to identify relevant methods of implementation of the theoretical method. The chapter is arranged on following sub topics: impact of behavior on paintings, investigation of methods and results of intervention.



### Chapter Six: Investigation of applicability of stabilization: case studies

This chapter consists of descriptions about research done in specific sites. It deals with the applicability of selected methods of intervention on selected sites. Investigation done in each site is described separately with developed conservation plans. The chapter contains material on following topics: methodology of investigation, findings and plans of preservation.

### Chapter Seven: Systematic conservation of mural paintings

The final chapter contains conclusions drawn out from analyses. This discussion is divided into following topics: analyses necessary in preservation, relevant actions of intervention, methods of repair of defects, methodology of minimization of decay and stabilization of monuments in the built environment by enhancing their user values. Procedures of preservation of different paintings are described in detail.



University of Moratuwa, Sri Lanka.  
Electronic Theses & Dissertations  
[www.lib.mrt.ac.lk](http://www.lib.mrt.ac.lk)